




## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>5</sup> :</b>  <b>D04H 1/48, 13/00, 1/70</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 93/15247</b>  <b>(43) International Publication Date:</b> <b>5 August 1993 (05.08.93)</b>
<b>(21) International Application Number:</b> PCT/US93/00566 <b>(22) International Filing Date:</b> 22 January 1993 (22.01.93) <b>(30) Priority data:</b> 825,016                      24 January 1992 (24.01.92)      US <b>(60) Parent Application or Grant</b> (63) Related by Continuation US                                      825,016 (CIP) Filed on                              24 January 1992 (24.01.92) <b>(71) Applicant (for all designated States except US):</b> FIBERWEB NORTH AMERICA, INC. [US/US]; 840 S.E. Main Street, Simpsonville, SC 29681 (US).		<b>(72) Inventors; and</b> <b>(75) Inventors/Applicants (for US only) :</b> QUANTRILLE, Tho- mas, E. [US/US]; 304 Walker Way, Simpsonville, SC 29681 (US). AUSTIN, Jared, A. [US/US]; 605 Sugar Mill Road, Greer, SC 29650 (US). GESSNER, Scott, L. [US/US]; 3110 Via Ve Caballo, Olivenhain, CA 92024 (US). <b>(74) Agents:</b> LINKER, Raymond, O., Jr. et al.; Bell, Seltzer, Park & Gibson, P.O. Drawer 34009, Charlotte, NC 28234 (US). <b>(81) Designated States:</b> AU, BR, CA, JP, KR, US, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).  <b>Published</b> <i>With international search report.</i>

**(54) Title:** PROCESS STABLE NONWOVEN FABRIC**(57) Abstract**

The invention provides elastic fabrics which are substantially non-extensible in the machine direction and have substantial elastic properties in the cross-machine direction. The process stable fabrics of the invention include a net and a fibrous layer which are secured together. The net is composed of a plurality of continuous machine direction strands and a plurality of cross-direction strands. The machine direction strands are substantially non-extensible and the cross-direction strands are substantially elastic. The fabrics of the invention can be manufactured and processed more readily than fabrics which are elastic in both the machine direction and the cross-machine direction.

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	FR	France	MR	Mauritania
AU	Australia	GA	Gabon	MW	Malawi
BB	Barbados	GB	United Kingdom	NL	Netherlands
BE	Belgium	GN	Guinea	NO	Norway
BF	Burkina Faso	GR	Greece	NZ	New Zealand
BG	Bulgaria	HU	Hungary	PL	Poland
BJ	Benin	IE	Ireland	PT	Portugal
BR	Brazil	IT	Italy	RO	Romania
CA	Canada	JP	Japan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SK	Slovak Republic
CI	Côte d'Ivoire	LI	Liechtenstein	SN	Senegal
CM	Cameroon	LK	Sri Lanka	SU	Soviet Union
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	MC	Monaco	TG	Togo
DE	Germany	MG	Madagascar	UA	Ukraine
DK	Denmark	ML	Mali	US	United States of America
ES	Spain	MN	Mongolia	VN	Viet Nam
FI	Finland				

## PROCESS STABLE NONWOVEN FABRIC

### Field of the Invention

The invention relates to process stable composite elastic nonwoven fabrics and to processes for producing them. More specifically, the invention  
5 relates to process stable composite nonwoven elastic fabrics having desirable strength, conformability, and stretch and recovery properties, and which can be more readily manufactured and processed using existing textile equipment as compared to prior nonwoven  
10 fabrics.

### Background of the Invention

Nonwoven elastic fabrics have been the subject of considerable attention and effort. Elastic fabrics are desirable for use in bandaging materials,  
15 garments, diapers, supportive clothing and personal hygiene products because of their ability to conform to irregular shapes and to allow more freedom of body movement than fabrics with limited extensibility.

Elastomeric materials have been incorporated  
20 into various fabric structures to provide stretchable fabrics. In many instances, such as where the fabrics are made by knitting or weaving, there can be a relatively high cost associated with the fabric. In cases where the fabrics are made using nonwoven  
25 technologies, the fabric can suffer from insufficient

-2-

strength and only limited stretch and recovery properties.

Elastomers used to fabricate elastic fabrics often have an undesirable rubbery feel. This is particularly true with thermoplastic elastomers rather than cross-linked elastomers. When these materials are used in composite nonwoven fabrics, the hand and texture of the fabric can be perceived by the user as sticky or rubbery and therefore undesirable.

10 Nonwoven fabrics having thermoplastic elastomers incorporated into the fabric structure can be extremely difficult to process and to manufacture. For example, tension control during fabric manufacture and/or during downstream processing can be extremely  
15 critical. A small change in tension can result in stretching or recovery of the fabric which can lead to a non-uniformly manufactured product. Tension control is even more aggravated when heating is required, for example, during fabric drying, adhesive application,  
20 lamination, thermal bonding or other thermal treatment. When subjected to heat and tension, the fabric can stretch and otherwise undergo greater distortion than when the fabric is at room temperature. In addition, thermoplastic elastomers can lose elastic properties  
25 when stressed at elevated temperatures and allowed to cool fully or partially while stressed, and/or the thermoplastic fibers and filaments are apt to break, thereby causing the elastic fabric to lose a portion or all of its elastic properties. Still further, when  
30 elastic fabrics are wound into rolls, stretching of the fabrics can occur during the winding process and the fabric can lose elastic properties during its subsequent storage due to the phenomenon of creep.

U.S. Patent 4,775,579 to Hagy, et al.  
35 discloses desirable composite elastic nonwoven fabrics containing staple textile fibers intimately hydroentangled with an elastic web or elastic net. One

-3-

or more webs of staple textile fibers and/or wood pulp fibers can be hydroentangled with an elastic net according to the disclosure of this invention. The resulting composite fabric exhibits characteristics comparable to those of knit textile cloth and possesses superior softness and extensibility properties. The rubbery feel traditionally associated with elastomeric materials can be minimized or eliminated in these fabrics.

10 U.S. Patent 4,413,623 to Pieniak discloses a laminated structure such as a disposable diaper which can incorporate an elastic net into portions of the structure. The elastic net can be inserted in a stretch position between first and second layers of the structure and bonded to the layers while in the stretch condition. Subsequent relaxation of the elastic net can result in gathering of the structure.

U.S. Patent 4,525,407 to Ness discloses elastic fabrics which include an elastic member which may be an elastic net intermittently bonded to a substrate which prior to stretching is less easily extensible than the elastic member. The non-elastic member is bonded to the elastic member and the entire composite is rendered elastic by stretching and relaxation.

U.S. Patent 4,606,964 to Wideman discloses a bulk composite web which can be prepared by bonding a gatherable web to a differentially stretched elastic net. Subsequent relaxation of the differentially stretch net is said to result in gathering of the fabric.

The various problems associated with thermoplastic elastomeric materials, as discussed previously, render many of these and other composite elastic fabrics difficult to manufacture and process. There are problems with tension control, elongation under the tension induced by converting machines,

-4-

irregular cut length, poor tracking, blocking, and similar problems. In the past, these problems have been overcome or minimized only with substantial difficulty. To minimize the problem of machine  
5 direction stretching during fabric converting and/or forming, typical approaches have been to either cool the thermoplastic elastomer to a temperature below its glass transition temperature or to make "heat  
activated" materials that are rigid, but then shrink  
10 and become elastomeric when heated. These steps are often required to process the material under acceptable tension levels even at ambient temperatures. Alternative process modifications have required extremely exact tension control mechanisms; but these  
15 do not consistently eliminate problems during normal fabric processing.

#### Summary of the Invention

The invention provides process stable composite elastic fabrics which can be readily  
20 processed on existing textile apparatus without requiring special tension control mechanisms and without substantial harm to the elastic properties of the fabric. The fabrics can be subjected to heat during the process of manufacturing the fabrics or  
25 thereafter without destruction of elastic properties. Thus, elastic fabrics of the invention can be manufactured in a more convenient and straightforward manner and can be processed thereafter with less restrictions and/or fabric damage than prior elastic  
30 fabrics.

The process stable composite elastic fabrics of the invention are substantially non-extensible in the machine direction and have substantial elastic properties in the cross-machine direction. Thus, the  
35 process stable fabrics of the invention can be stressed in the machine direction without substantial fabric stretching and without requiring specialized processes

-5-

and/or apparatus to compensate for elastic stretching. Moreover, because elastomeric components of the fabric are not substantially stretched when the fabric is stressed in the machine direction, thermal treatments  
5 can be more readily applied to the fabric without substantial fabric harm as a result of combined thermal and stress effects.

The process stable composite elastic fabrics of the invention have a predetermined width and an  
10 indeterminate length which is substantially greater than the width of the fabric. The width of the fabric defines the fabric's cross-machine direction and the length of the fabric defines the machine direction of the fabric. The composite nonwoven fabric includes at  
15 least one fibrous layer and a net combined with the fibrous layer. The net is composed of a plurality of continuous machine direction strands oriented in substantially the machine direction of the fabric and a plurality of cross-direction continuous strands  
20 oriented in substantially the cross direction of the fabric. The machine direction strands are substantially non-extensible and preferably are substantially non-extensible under applied stress at temperatures of up to 70°C or higher. The cross-  
25 direction strands comprise a substantial amount of a thermoplastic elastomer, preferably about 20 wt. %, more preferably at least about 50 wt. %, such that the net is elastic in the cross-direction. In one preferred embodiment, the net is combined with the  
30 fibrous web by hydroentangling. The net can alternatively be combined with the fibrous web by adhesive or thermal bonding. Advantageously, the fibrous web comprises staple fibers including  
35 cotton, wool and wood pulp fibers. These fibers can provide desirable aesthetic qualities to the composite

-6-

fabric. Additionally or alternatively the fibrous web can comprise a spunbond or a meltblown web.

Advantageously, the machine direction continuous strands employed in the net component of the composite fibrous web are formed of a crystalline polymer such as a crystallizable polyolefin material which is strong and which readily adheres to the thermoplastic elastomer material used in the cross machine direction strands of the net. In one particularly preferred embodiment of the invention, the net is formed from polyolefin strands oriented in the machine direction and the cross machine direction strands are formed from a thermoplastic styrenic elastomer.

As compared to nonwoven fabrics which are either non-elastic or fully elastic, the composite fabrics of the invention have various advantages and benefits. As compared to non-elastic fabrics, the fabrics of the invention are advantageous in providing elastic properties in the cross-machine direction. As compared to conventional elastic nonwoven fabrics which are elastic in both the machine direction and the cross-machine direction, the fabrics of the invention provide significant benefits and advantages both in terms of their manufacture and their subsequent use. The fabrics of the invention can be manufactured and processed without the need for specialized tension control. When thermally treated while being processed in the machine direction, the fabrics of the invention typically do not lose elastic properties because the elastic filaments are not subjected to tensioning. The fabrics of the invention can be readily cut without deformation during the cutting process so that the cut length can be more accurately controlled. Similarly the fabric of the invention allows for more accurate treatment and control in other converting processes. The fabrics of the invention can be readily wound and



-7-

stored in roll form under various environmental conditions without subjecting the elastic components of the fabric to stresses which would result in creep of the fabric. In addition, the fabrics of the invention  
5 can provide significant aesthetic benefits including differential drape, curl and shear properties which are not readily provided in fully elastic and fully non-elastic composite fabrics.

#### Brief Description of the Drawings

10 In the drawings which form a portion of the original disclosure of the invention:

Figure 1 illustrates in perspective view a net in roll form which can be used in producing fabrics of the invention;

15 Figure 2 is a schematic illustration of one preferred process for producing a fabric in accordance with the invention;

Figure 3 is an exploded view of one preferred fabric according to the invention;

20 Figure 4 is a schematic illustration of a process wherein a fabric of the invention is laminated to a second fabric or film layer; and

Figure 5 illustrates the results of thermomechanical analysis conducted on filaments  
25 composed of styrenic elastomers, EVA polymer and LLDPE polymer.

#### Detailed Description of the Invention

In the following detailed description of the invention, specific preferred embodiments of the  
30 invention are described to enable a full and complete understanding of the invention. It will be recognized that it is not intended to limit the invention to the particular preferred embodiments described, and although specific terms are employed in describing the  
35 invention, these terms are used for the purpose of illustration and not for the purpose of limitation. It will be apparent that the invention is susceptible to

-8-

variations and changes within the spirit of the teachings herein.

Figure 1 illustrates an elastomeric net 10 having a plurality of substantially continuous strands or filaments oriented in the machine direction of the fabric as indicated by arrow 12 and a plurality of substantially continuous filaments or strands oriented in the cross-machine direction, that is, the width direction of the fabric as indicated by arrow 14. The strands oriented in the machine direction are substantially non-extensible strands while the strands in the cross machine direction are substantially elastic and preferably comprise a thermoplastic elastomer. As used herein and only for purposes of this application, the term "elastic" is used to mean strands and/or fabrics capable of substantially complete recovery, i.e. greater than about 75%, preferably greater than about 90% recovery, when stretched in an amount of about 10% at room temperature expressed as:

$$\% \text{ recovery} = (L_s - L_r) / (L_s - L_o) \times 100$$

where:  $L_s$  represents stretched length;  $L_r$  represents recovered length measured one minute after recovery; and  $L_o$  represents original length of material.

As used herein and only for the purposes of this application, the term "substantially non-extensible" is used to mean filaments and/or strands which, at 25°C exhibit an extensibility of 2% or less, preferably about 1% or less when subjected to an applied stress of 5 mg/denier which is a stress based on stresses applied to a fabric by fabric conversion apparatus. In preferred embodiments of this invention, substantially non-extensible filaments and strands have an extensibility of less than about 5% at 70°C under an applied stress of 5 mg/den.

Generally, it is desirable that the number of strands per inch in each of the machine and cross-

-9-

machine directions of the net range from between about 2 and about 30 strands per inch preferably from 5 to about 20 strands per inch although greater numbers of filaments can be employed where desirable. Typically, the elastomeric net 10 will have a basis weight ranging from about 15 grams per square meter to about 200 grams per square meter, more preferably from about 50 to about 90 grams per square meter, and can employ filaments having diameters ranging from about 50 to about 600 microns, preferably from about 150 to about 400 microns.

The elastic net 10 can be prepared by any of various well known processes including the process disclosed in U.S. Patent 4,636,419, issued January 13, 1987 to Madsen, et al., incorporated herein by reference. In general, the elastic net is made by extruding a plurality of substantially non-extensible polymeric strands in the machine direction while simultaneously or thereafter extruding and joining to said machine direction filaments, a plurality of elastic polymeric strands oriented substantially in the cross machine direction.

The elastic material making up the strands in the cross-machine direction of the net normally comprise at least one thermoplastic elastomer. Suitable thermoplastic elastomers include the diblock, triblock, radial and star copolymers based on polystyrene (S) and unsaturated or fully hydrogenated rubber blocks. The rubber block can consist of butadiene (B), isoprene (I), or the hydrogenated version, ethylene-butylene (EB). For example, S-B, S-I, S-EB, as well as S-B-S, S-I-S, S-EB-S linear block copolymers can be used. Typically when used one or more of the diblock copolymers are blended with the triblock or radial copolymer elastomers. Preferred thermoplastic elastomers of this type can include the KRATON polymers sold by Shell Chemical Company or the

-10-

VECTOR polymers sold by DEXCO. Other elastomeric thermoplastic polymers include polyurethane elastomeric materials such as ESTANE sold by BF Goodrich Company; polyester elastomers such as HYTREL sold by E. I. Du Pont De Nemours Company; polyetherester elastomeric materials such as ARNITEL sold by Akzo Plastics; and polyetheramide elastomeric materials such as PEBAX sold by ATO Chemie Company; and the like.

The elastic strands in the cross-machine direction of the elastic net 10 can also be prepared from blends of thermoplastic elastomers with other polymers such as polyolefin polymers, e.g. blends of Kraton polymers with polyolefins such as polypropylene and polyethylene, and the like. These polymers can provide lubrication and decrease the melt viscosity, allow for lower melt pressures and temperatures and/or increase throughput, and provide better bonding properties too. In a preferred embodiment of the invention, such other polymers can be included in the blend as a minor component, for example in an amount of between about 5% by weight up to 50% by weight, preferably from about 10 to about 30% by weight of the mixture. Suitable thermoplastic polymers, include, in addition to the polyolefin polymers, poly(ethylene-vinyl acetate) polymers having an ethylene content of up to about 50% by weight, preferably between 15 and 30% by weight and copolymers of ethylene and acrylic acid or esters thereof, such as poly(ethylene-methyl acrylate) or poly(ethylene-ethyl acrylate) wherein the acrylate acid or ester component ranges from about 5 to about 50% by weight, preferably from about 15 to about 30% by weight. In addition polystyrene and poly(alpha-methyl styrene) can be used.

The machine direction substantially non-extensible strands constitute a non-elastic polymeric material including any of the various well known filament-forming polymers, such as polyolefins

-11-

including polyethylene, polypropylene, linear low density polyethylene (LLDPE); polyesters such as polyethylene terephthalate; polyamides such as nylon-6 and nylon-6,6; copolymers, blends of such materials and the like. Preferably the non-elastic polymer is a crystalline material which provides a filament with a high tenacity and a relatively sharp melting point. Advantageously, the substantially non-extensible strands in the machine direction are composed of a material which adheres readily to the elastic strands in the cross-machine direction. In this regard it is desirable that there be substantial bonding between the strands in the machine direction and the strands in the cross-machine direction. Generally, a polyolefin material is preferably used for the machine direction strands when the cross-machine direction strands are styrene-based elastomeric materials. Nylon continuous machine direction can be advantageously employed in combination with polyetheramide elastomeric cross-machine direction strands. Polyester-based strands advantageously can be used as machine direction strands in combination with polyetherester elastomeric cross-machine direction strands.

In one preferred embodiment of the invention, the machine direction substantially non-extensible strands can comprise an adherence promoting additive to improve the adherence of the machine direction strands to the cross-machine direction strands. Preferred additives to improve adherence include poly(ethylene-vinyl acetate) polymers having an ethylene content of up to about 50% by weight, preferably between about 15 and about 30% by weight, and copolymers of ethylene and acrylic acid or esters thereof, such as poly(ethylene-methyl acrylate) or poly(ethyl acrylate) wherein the acrylic acid or ester component ranges from about 5 to about 50% by weight, preferably from about 15 to 30% by weight. These materials are preferably included in the

-12-

machine direction strands in an amount of between about 2 and about 50% by weight, preferably between about 10 and about 30% by weight depending on the primary component of the strand. In addition other materials  
5 such as plasticizers, tackifiers, talc, and the like can be compounded into the resin at low levels to promote bonding. As indicated previously, the machine direction strands are preferably stable under applied stress at high temperatures. However, if such  
10 additives are included in too great an amount the thermal stability of the machine direction strands can suffer.

Figure 2 illustrates one preferred process for forming a composite fabric of the invention. A  
15 carding apparatus 20 forms a first carded layer 22 onto forming screen 24. Carded fibrous layer 22 can comprise any of various well-know synthetic or natural fibers, and in one preferred embodiment of the invention, also includes binder fibers in an amount of  
20 between about 5% and about 50% by weight. The web 22 is moved by forming screen 24 in the machine direction by rolls 26.

A conventional supply system thereafter applies the elastomeric net 10 onto the moving carded  
25 layer 22. As discussed previously, the elastomeric net 10 includes spaced apart machine direction and cross machine direction strands which intersect to form apertures. Although it is preferred that the net have a substantially regular, rectangular shape, irregular  
30 geometry nets such as diamond-shaped nets and the like can be used wherein the non-elastic strands are oriented primarily in the machine direction and elastic strands are oriented primarily in the cross machine direction. A roll 28 applies tension to the two-  
35 layered structure 30 which is formed from the combination of the carded layer 22 and the net layer

-13-

10. The two layer structure is advanced in the machine direction by forming screen 24.

A second carding apparatus 32 deposits a second carded fibrous layer 34 comprising synthetic and/or natural fibers onto the two layer structure 30 to thereby form a three-layer composite structure 36 consisting of a carded web/elastomeric net/carded web. The synthetic and/or natural fibers making up carded web 34 can be the same or different as compared to the fibers in carded web 22. The three-layer composite web 36 is conveyed in the machine direction by the combination of forming screen 24 and roll 38. It will be apparent to the skilled artisan that the composite structure including net 10 is subjected to tension between the forming rolls 28 and 38. Because the machine direction strands in the net 10 are substantially non-extensible strands, the tension applied between rolls 28 and 38 does not result in substantial stretching of the net 10 and hence there is little or no stretching of the composite elastic structure 36.

The composite structure 36 is thereafter conveyed in the machine direction as shown in Figure 1 to a hydroentangling station 40 wherein a plurality of manifolds 42, each including one or more rows of fine orifices, direct high pressure jets of liquid through composite web 36 to intimately hydroentangle the fibers in each of the layers 22 and 34 with each other and with net 10. As a result of the hydroentangling treatment, at least a portion of the fibers in each of the carded layers 22 and 34 preferably extend through apertures in the net and into the carded layer on the other side of the net.

The hydroentangling station 40 is constructed in a conventional manner as known to the skilled artisan and as described, for example, in U.S. Patent 3,485,706 to Evans, which is hereby incorporated by

-14-

reference. As known to the skilled artisan, fiber hydroentanglement is accomplished by jetting liquid, typically water, supplied at a pressure from about 200 psig up to about 1,800 psig or greater, to form fine, essentially columnar liquid streams. The high pressure liquid streams are directed to at least one surface of the composite layered structure. The composite is supported on a foraminous support screen 44 which can have a pattern to form a nonwoven structure with a pattern or with apertures, or the screen 44 can be designed and arranged to form a hydraulically entangled composite which is not patterned or apertured. The laminate can be passed through a second hydraulic entangling station schematically illustrated in Figure 2 by manifolds 46, to enable hydraulic entanglement on the other side of the composite web fabric.

During the hydraulic entanglement treatment, the fibers in the carded layer or layers are forced into and/or through the elastomeric net 10, thereby securing the carded fibrous layer to the elastomeric net. Preferably, the hydroentangling treatment is sufficient to force the fibers present in at least one or the layers 22 and 34 into and/or through the apertures in the elastomeric net 10. More preferably, the hydroentangling treatment is sufficient to force at least portion of the fibers in both carded layers 22 and 34 into and/or through the apertures in the elastomeric net.

The elastomeric web 10 remains in a substantially planer arrangement during the hydroentangling treatment. Thus, the machine direction and cross-machine direction filaments, respectively, of the elastomeric net undergo little if any movement in the cross-sectional direction, i.e. in the Z direction within the web. Thus, the elastomeric net remains within a discrete interior cross-sectional portion of the composite web.



-15-

A condensed, hydraulically entangled composite web 48 is removed from the hydroentangling station 40 via roll 50 which cooperates with forming wire 44 and forming web rolls 52. The tension applied to the composite web 48 by rolls 50 and 52 does not result in substantial stretching of the elastomeric composite 48 because the machine direction strands of the net 10 are substantially non-extensible.

The web 48 exiting the hydroentangling station is thereafter preferably dried at a conventional drying station (not shown) and thereafter may be thermally treated at an optional thermal treatment station 54, shown in Figure 2 as heated calender rolls 56 and 58. The optional thermal treatment station 54 is used when binder fibers or another binder material is present in the composite web 48. The operating temperature of the heated rolls 56 and 58 is adjusted to a surface temperature such that the binder fibers or other binder materials present in the composite web 48 are thermally activated to bind the composite web 48 into a coherent, unitary structure. In accordance with the present invention, the thermal treatment can be more readily carried out because the elastomeric strands in the net 10 are not subjected to tension during the thermal treating process. Preferably, the operating temperature of the rolls 56 and 58 is maintained below a temperature which would cause thermal degradation or melting of the elastomeric materials in the net 10.

The composite web 60 is removed from the nip of rolls 56 and 58 and is wound by conventional means onto roll 62. The composite elastic web 60 can be stored on roll 62 without substantial harm to the fabric due to the phenomenon of creep; that is, deformation that is time dependent and is exhibited by many elastomeric materials subjected to a continuing load. In many cases, creep deformation may not be

-16-

recoverable following removal of the applied load. With the fabric 60 stored on roll 62, the elastomeric filaments of net 10 are only found in the cross-machine direction of the net and therefore are not subjected to stress during storage on roll form. The fabric 60 stored on roll 62 may be immediately or later passed to end use manufacturing processes, for example, for use in bandages, diapers, disposable undergarments, personal hygiene products, and the like.

10           The method illustrated in Figure 2 is susceptible to numerous preferred variations. For example, although the schematic illustration of Figure 2 shows carded webs being formed directly during the in-line process, it will be apparent that the carded webs can be preformed and supplied as rolls of preformed webs. Similarly, although the elastomeric net is shown being supplied as a roll of preformed net, the net can be formed directly in-line. Similarly, although Figure 1 illustrates the use of carded fibrous webs both above and below the net 10, only a single fibrous web such as web 22 can be employed or more than two fibrous webs can be employed. Moreover, it will be apparent to the skilled artisan that fibrous webs can be manufactured and supplied by other well known processes such as air-laying and the like.

          The hydroentanglement station 40 is a preferred process step for securing the elastomeric net 10 to one or more fibrous webs 22, 34. However, in other preferred embodiments of the invention, the fibrous webs 22 and/or 24 can be secured to elastomeric net 10 by lamination including solvent-based adhesive and/or thermal adhesive lamination, needling and/or other well known textile processes.

          The heated calender rolls 56 and 58 can, in other embodiments of the invention, be replaced by other thermal activations zones, for example in the form of a through-air bonding oven or in the form of a

-17-

microwave or other RF treatment zone. An especially preferred through-air bonding or through-air drying treatment zone employs support screens both above and below the fabric which contact both surfaces of the fabric during passage through the oven. The screens are advantageously metallic screens resulting in conductive heating of both fabric surfaces by contact with the upper and lower metal screens respectively. Other heating stations such as ultrasonic welding stations can also be advantageously used in the invention. Such conventional heating stations are known to those skilled in the art and are capable of effecting substantial heating of the fabric sufficient for thermal activation of binder fibers when such fibers are incorporated into the fabric.

As indicated previously, nonwoven webs other than carded webs are also advantageously employed in the production of fabrics according to the invention. Nonwoven staple webs can be formed by air laying, garnetting, wet laying, and similar processes known in the art. Spunbonded webs which are extensible in the cross-machine direction because of little or no filament-to-filament bonding can be substituted for either or both of the carded webs illustrated in Figure 2 and/or can be used in combination with one or both of the carded webs. Similarly meltblown webs which are extensible in the cross machine direction can be substituted for and/or used in conjunction with either of carded webs 22 and 34 shown in Figure 2.

Figure 3 illustrates an exploded view of the three-layered structure 36 of Figure 2 prior to hydroentanglement. Each of webs 22 and 34 include staple and/or natural fibers such as fibers formed from polyester, polyolefins such as polypropylene or polyethylene, nylon, acrylic, modacrylic, rayon, cellulose acetate, biodegradable synthetics such as a biodegradable polyester, aramide, fluorocarbons,

-18-

polyphenylene sulfide staple fibers and the like. Preferred natural fibers include wool, cotton, wood pulp fibers and the like. Blends of such fibers can also be used. In addition, all or a portion of the  
5 staple fibers can be glass, carbon fibers and the like.

The webs 22 and 34 can also include binder fibers in an amount of between about 5 and about 50 wt. %. Binder fibers are known in the art and include fibers made from low melting polyolefins such as  
10 polyethylenes; polyamides and particularly co-polyamides; polyesters and particularly copolyesters; acrylics and the like. The binder fibers, when used, preferably have a lower activation temperature than the melting point of the net. In the case that the binder  
15 fibers activate above the glass transition temperature of the hard segment of the thermoplastic elastomer contained in the net, then heating conditions are advantageously closely controlled to activate the binder fibers without degrading or deforming the net.

20 Particularly preferred binder fibers include bicomponent and multi-component fibers such as sheath/core, side-by-side, sectorized or similar bicomponent fibers wherein at least one component of the fiber is a low melting material such as  
25 polyethylene, a copolyester, a copolyamide or the like. Preferred bicomponent fibers have a melting temperature for the binder portion of the fiber in range of between about 100 and about 135°C. Such fibers include polypropylene/polyethylene and polyester/polyethylene  
30 sheath/core fibers and polyester/copolyester sheath/core fibers. One particularly preferred binder fiber is a copolyester/polyester sheath/core fiber having a melting point of about 110°C commercially available from Hoechst-Celanese Corporation as "K-54".

35 As indicated previously, the fabrics of the invention can also incorporate spunbonded nonwovens including polyolefin, nylon, polyester, copolymers of

the same and other webs as are known to those skilled in the art. Similarly, meltblown nonwovens including both elastomeric and non-elastomeric meltblown webs prepared from polyolefins, nylons, polyesters, random  
5 and block copolymers, elastomers and the like can also be included in fabrics of the invention.

Figure 4 illustrates an exemplary end-use process for a fabric 60 of the invention. The fabric 60 is substantially elastic in the cross-machine  
10 direction as indicated by arrow 70 and is substantially non-extensible in the machine direction as illustrated by arrow 72. The fabric 60 can be supplied via a roll to a lamination process as illustrated in Figure 4. A second film or fabric 74 is supplied from roll 76 for  
15 lamination with the fabric 60. An adhesive material may be applied to the film or fabric 74 via one or more rolls 78 by conventional apparatus known to the those skilled in the art. A pair of calender rolls 80 and  
20 fabric 74 to the elastic fabric 60 of the invention.

As is apparent to the skilled artisan, during the lamination process illustrated in Figure 4, the fabric 60 is subjected to tension in the machine direction. During a typical lamination process, if an  
25 elastic fabric is stretched due to elasticity, the film or fabric layer 74 will be gathered following relaxation of the laminate. In addition, as discussed below, when elastomeric materials are stretched during heating, for example, by contact with heated calender  
30 rolls 80 and 82, a failure of elastic properties can result.

Figure 5 illustrates the results of thermal stress tests conducted on filaments of a styrenic elastomer having a denier per filament of 1283 (1426  
35 dtex); a filament composed of poly(ethylene vinyl acetate) having a denier of 530 (589 dtex) and on a filament of linear low density polyethylene having a

-20-

denier of 844 (937 dtex). Each of the filaments was subjected to a constant stress of 4.2 mg/den (37  $\mu$ N/dtex) and subjected to different thermal environments. As seen in Figure 5, the elastomeric filaments undergo substantial elongation even at room temperature (20°C). At 70°C, the ethylene vinyl acetate filaments exhibit substantial elongation. At 90°C, the elastomeric filament was broken while the ethylene vinyl acetate filament was broken at 80°C.

10 The filament composed of linear low density polyethylene, on the other hand, exhibited substantial stability even at a temperature of 100°C. It will be apparent that the stress employed in this series of tests (approximately 4 mg/den) is an extremely low

15 stress. It will also be apparent that elastomeric filaments are highly unstable when subjected to the combination of even a low stress together with elevated with thermal treatment.

The data illustrated in Figure 5 is set forth

20 below, in Table 1 in tabular form.

TABLE 1 PERCENT ELONGATION VS. TEMPERATURE

TEMPERATURE (°C)		PERCENT ELONGATION		
		STYRENIC ELASTOMER	EVA	LLDPE
20		5.5	0.6	0.6
30		6.5	0.9	0.9
40		7.0	1.3	1.1
50		7.8	1.9	1.5
60		10.0	3.4	1.9
70		14.7	6.4	2.3
80		28.9	19.1	2.8
90		34.6	Break	3.5
100		Break	Break	4.4
110		Break	Break	6.1
ADDITIONAL INFORMATION				
Filament Size	denier	1283	530	844
	dtex	1426	589	937
Stress	mg/den	4.21	4.23	4.23
	μN/dtex	37.2	37.4	37.4

As is apparent from the data presented above, nonwoven fabrics with elastomeric materials in the machine direction are difficult to process. In the thermomechanical analysis test, above, the tension presented to the materials is extremely low and is lower than tensions typically achieved on forming and converting equipment. However, as is apparent from the above, even at room temperature and under this unrealistically low tension, elastomeric filaments still stretch 5-6%. In the processing and/or converting environment, such stretching can interfere with steps such as cutting and the like. However, with the elastomeric fabrics of the invention, the fabrics

-22-

can be processed in the machine direction without stretching.

The following examples illustrate preparation of preferred fabrics according to the invention:

5

## EXAMPLE 1

In Example 1, a process-stable nonwoven fabric was made by using a rectangular net with 18 strands/inch in the MD and 9 strands/inch in the CD. This net had linear low density polyethylene in the MD and elastomer in the CD. The elastomer in the CD is a styrenic triblock thermoplastic rubber consisting of SIS and SBS rubber compounded with a low molecular weight polystyrene. The nonwoven composite was made by hydroentangling a polyester fiber blend consisting of 15 70% by weight Type 183, 1.5 dpf x 1.5" PET from Hoechst Celanese and 30% by weight Type K-54 2.0 dpf x 1.5" bicomponent fiber also from Hoechst Celanese. After entangling, the product was through-air bonded at 320°F. Note that this bonding step could not have been 20 performed if the product was not process stable under heat and tension. The resulting product was soft, had good CD elasticity, and was resistant to fiber pilling and fuzzing.

## EXAMPLE 2

25

In Example 2, a process-stable nonwoven fabric was made by using a rectangular net with 12 strands/inch in the MD and 12 strands/inch in the CD. In the MD, this net was 80% low density polyethylene (copolymer) and 20% ethylene-vinyl acetate copolymer. 30 An SIS and SBS rubber compound blended with low molecular weight polystyrene was used as the elastomer.

The product was entangled with a fiber blend consisting of 70% by weight Type 182, 2.2 dpf x 1.5" Polypropylene from Hercules, and 30% by weight Type K- 35 54 2.0 dpf x 1.5" bicomponent fiber from Hoechst Celanese.



-23-

The resulting product had a very soft hand and good CD stretch.

### EXAMPLE 3

In example 3, a process-stable non-woven fabric was made just like example 2. After forming the web, however, the product was subsequently calender bonded. A micro-gapped, open-nip calender with two smooth rolls was used to bond the fibers with minimal effect on the net.

### 10 EXAMPLES 4, 5 AND 6

Examples 4, 5 and 6 were all made in a similar fashion. The difference between examples is the net used. Examples 3 used an 18 x 3 net, example 4 used an 18 x 5 and example 5 used an 18 x 7. All nets had a 50/50 blend of EVA with a low density polyethylene (copolymer) as the MD resin, and for the CD resin, the same SIS-SBS rubber compound used in the previous examples.

### EXAMPLE 7

20 Example 7 was made by taking a 15 x 8 net. This net had a rectangular (rather than circular) MD strand geometry. The net consisted of an 80/20 blend of a low density polyethylene (copolymer) with EVA as the MD resin. Again for the CD resin the same SIS-SBS rubber compound was used as in the previous examples.

This product was entangled with a fiber blend consisting of 70% by weight 1.0 dpf x 1.5" polypropylene staple, and 30% by weight Type K-54 2.0 dpf x 1.5" bicomponent fiber from Hoechst Celanese. A micro-gapped, open-nip calender with two smooth rolls was used to bond the fibers with minimal effect on the net.

The invention has been described in considerable detail with reference to its preferred embodiments. It will be apparent however that the invention is susceptible to numerous modifications and variation without departure from the spirit and scope

-24-

of the invention as described in the foregoing specification and defined in the appended claims.

-25-

## CLAIMS:

1. A process stable composite elastic fabric of predetermined width and having a length substantially greater than said width, said width defining the cross-machine direction of said fabric and  
5 said length defining the machine direction of said fabric, said composite fabric comprising:  
at least one fibrous layer; and  
a net combined with said fibrous layer, said net comprising a plurality of continuous machine  
10 direction strands oriented in substantially the machine direction of said fabric and a plurality of cross-machine direction strands oriented in substantially the cross-machine direction of said fabric, said machine direction strands being substantially non-extensible  
15 and said cross-machine direction strands being elastic.
2. The process stable composite elastic fabric of Claim 1 wherein said machine direction strands have an extensibility of less than about 5% under an applied stress of 5 mg/den at temperatures of  
20 up to about 70°C.
3. The process stable fabric of Claim 1 wherein said cross-machine direction strands comprise at least about 20 wt. % of a thermoplastic elastomer.
4. The process stable fabric of Claim 3  
25 wherein said net is combined with said fibrous web by hydroentangling.
5. The process stable elastic fabric of Claim 1 wherein said fibrous web comprises staple fibers.

-26-

6. The process stable fabric of Claim 5 wherein said staple fibers are selected from the group consisting of polyolefins, polyesters, nylon, cotton, wood pulp and wool fibers.

5 7. The process stable fabric of Claim 6 wherein said staple fibers comprise binder fibers in an amount of at least 5 wt. %.

8. The process stable fabric of Claim 1 wherein said fibrous web is combined with said elastic  
10 net by adhesive lamination.

9. The process stable fabric of Claim 8 wherein said fibrous web includes binder fibers.

10. The process stable fabric of Claim 9 wherein at least a portion of said binder fibers are  
15 thermally activated to bond said hydroentangled fabric into a coherent, substantially unitary structure.

11. A process stable composite elastic fabric of predetermined width and having a length substantially greater than said width, said width  
20 defining the cross-machine direction of said fabric and said length defining the machine direction of said fabric, said composite fabric comprising:

at least one fibrous layer comprising staple fibers; and

25 a net combined with said fibrous layer, said net comprising a plurality of continuous machine direction strands oriented in substantially the machine direction of said fabric and plurality of cross-machine direction strands oriented in substantially the cross-  
30 machine direction of said fabric, said machine direction strands being non-elastic and said cross-

-27-

machine direction strands comprising at least about 20 wt. % of a thermoplastic elastomer;

whereby said fabric is elastic in the cross-machine direction and is substantially non-extensible  
5 in the machine direction.

12. The process stable fabric of Claim 11 wherein said fibrous layer comprises staple fibers and wherein said net is combined with said fibrous layer by hydroentanglement.

10 13. The process stable composite elastic fabric of Claim 12 wherein said net comprises polyolefin strands oriented in the machine direction.

14. The process stable composite elastic fabric of Claim 13 wherein said cross-direction strands  
15 of said net comprise a styrene-based thermoplastic elastomer in an amount of at least about 50 wt. %.

15. The process stable composite elastic fabric of Claim 14 wherein said fibrous layer comprises at least about 5 wt. % binder fibers having been  
20 thermally activated to bond said hydroentangled fabric into a coherent, substantially unitary structure.

16. The process stable fabric of Claim 15 wherein said staple fibers in said fibrous web are selected from the group consisting of polyolefins,  
25 polyesters, nylon, cotton, wood pulp and wool fibers.

17. The process stable fabric of Claim 11 additionally comprising at least one spunbonded web combined with said fibrous layer and to said net.

-28-

18. The process stable fabric of Claim 11 additionally comprising at least one meltblown web combined with said fibrous layer and said net.

19. The process stable fabric of Claim 11  
5 wherein said machine direction strands of said net comprise linear low density polyethylene.

20. The process stable fabric of Claim 11 wherein said machine-direction strands of said net comprise an adhesive promoting additive.

10 21. The process for forming a process stable fabric comprising:

providing a fibrous nonwoven web;

providing a net comprising a plurality of continuous machine direction strands oriented in  
15 substantially the machine direction of said net and a plurality of cross-machine direction strands oriented substantially in the cross-machine direction of said net, said machine direction strands being substantially non-extensible and said cross-machine direction  
20 filaments being elastic; and

combining said fibrous web with said net to thereby form a non-woven fabric which is elastic in the cross-machine direction and which is substantially non-extensible in the machine direction.

25 22. The process of Claim 21 wherein said fibrous web is combined with said net by hydroentangling.

23. The process of Claim 22 wherein said fibrous web comprises staple fibers.

-29-

24. The process of Claim 23 wherein said fibrous layer comprises a carded layer of staple fibers.

25. The process of Claim 21 additionally comprising the step prior to said combining step, of providing a second fibrous web, and wherein said combining step is conducted to combine both of said fibrous webs with said net.

26. The process of Claim 22 wherein said fibrous web additionally comprises binder fibers.

27. The process of Claim 26 additionally comprising the step of thermally activating said binder fibers to thereby bond said web and said net into a coherent, substantially unitary structure.

28. The process of Claim 27 wherein said thermal activation step is conducted by contacting said fibrous layer with a heated surface.

29. The process of Claim 28 wherein said binder fibers comprise bicomponent fibers.

30. The process of Claim 21 additionally comprising the step, prior to said combining step of providing a nonwoven web selected from the group consisting spunbonded webs and meltblown webs and wherein said combining step is conducted to combine said fibrous web and said net with said additionally provided web.





FIG. 2.






FIG. 3.





FIG. 4.

FIG. 5.

## INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 93/00566

**I. CLASSIFICATION OF SUBJECT MATTER** (if several classification symbols apply, indicate all)<sup>6</sup>

According to International Patent Classification (IPC) or to both National Classification and IPC

Int.Cl. 5 D04H1/48; D04H13/00; D04H1/70

**II. FIELDS SEARCHED**Minimum Documentation Searched<sup>7</sup>

Classification System

Classification Symbols

Int.Cl. 5

D04H

Documentation Searched other than Minimum Documentation  
to the Extent that such Documents are Included in the Fields Searched<sup>8</sup>**III. DOCUMENTS CONSIDERED TO BE RELEVANT<sup>9</sup>**

Category <sup>10</sup>	Citation of Document, <sup>11</sup> with indication, where appropriate, of the relevant passages <sup>12</sup>	Relevant to Claim No. <sup>13</sup>
X	EP,A,0 007 802 (TEIJIN LTD) 6 February 1980	1,5,6,8
A	see whole document	3,4,7, 9-16, 19-23, 26-28
A	DE,A,2 364 958 (IMPERIAL CHEMICAL INDUSTRIES LTD.) 17 July 1975  see example 1	1,4-7, 9-12,15, 16, 21-17,29
A	US,A,4 863 779 (DAPONTE) 5 September 1989  see whole document	1,4,11, 15,17, 18,21, 22,25, 27,28
	-/--	

<sup>10</sup> Special categories of cited documents:<sup>10</sup> "A" document defining the general state of the art which is not considered to be of particular relevance<sup>10</sup> "E" earlier document but published on or after the international filing date<sup>10</sup> "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)<sup>10</sup> "O" document referring to an oral disclosure, use, exhibition or other means<sup>10</sup> "P" document published prior to the international filing date but later than the priority date claimed<sup>10</sup> "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention<sup>10</sup> "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step<sup>10</sup> "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.<sup>10</sup> "A" document member of the same patent family**IV. CERTIFICATION**

Date of the Actual Completion of the International Search

16 APRIL 1993

Date of Mailing of this International Search Report

93.05.33

International Searching Authority

EUROPEAN PATENT OFFICE

Signature of Authorized Officer

VAN BEURDEN-HOPKINS

## III. DOCUMENTS CONSIDERED TO BE RELEVANT (CONTINUED FROM THE SECOND SHEET)

Category *	Citation of Document, with indication, where appropriate, of the relevant passages	Relevant to Claim No.
A	US,A,4 775 579 (HAGY ET AL.) 4 October 1988 cited in the application see whole document -----	1,4-6, 11,21-25

**ANNEX TO THE INTERNATIONAL SEARCH REPORT  
ON INTERNATIONAL PATENT APPLICATION NO.**

US 9300566  
SA 69816

This annex lists the patent family members relating to the patent documents cited in the above-mentioned international search report. The members are as contained in the European Patent Office EDP file on  
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

16/04/93

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-0007802	06-02-80	JP-A- 55098956	28-07-80
		JP-C- 1370785	25-03-87
		JP-A- 55021420	15-02-80
		JP-B- 61037380	23-08-86
		US-A- 4296163	20-10-81
-----			
DE-A-2364958	17-07-75	None	
-----			
US-A-4863779	05-09-89	AU-A- 7049587	01-10-87
-----			
US-A-4775579	04-10-88	EP-A- 0315507	10-05-89
		JP-A- 1148856	12-06-89
-----			

**THIS PAGE BLANK (USPTO)**